

Wencon Ceramic Cream

General Description	<p>Wencon Ceramic Cream is a two-component compound. After curing, Wencon Ceramic Cream will exhibit a wide range of the characteristics of metals, which together with outstanding adhesion to all metallic surfaces, makes the compound highly suitable for repair of corroded and worn metal. Wencon Ceramic Cream is non conducting and will therefore not cause bi-metallic corrosion.</p> <p>Wencon Ceramic Cream has a high abrasion resistance, making it suitable for applications on propeller nozzles, rudders, thruster tunnels and housings. In addition, the product also offer high temperature resistance, which makes it ideal for applications on gas scrubbers, condensers and end-covers.</p>						
Surface Preparation	<p>Before applying, the surface must be clean. If possible shot blasted to Swedish Standard SA 2 1/2. Where impregnation of oil or salt is possible, the item is either left for 10-20 hours or heated to 30-40°C (86-104°F) in order to sweat out the oil or salt. Then the shot blasting is repeated. In some applications sandblasting is not possible and thorough grinding must take place to clean metal.</p> <p>N.B. Steel brushing is not advisable as it gives a smooth surface. After grinding Wencon Bio Cleaner is used for degreasing.</p>						
Mixing Ratio	Mixing ratio 1:2 by volume. Mix until even colour is obtained.						
Pot Life	30-40 minutes at 20°C (68°F), depending on amount.						
Applying	Wencon Ceramic Cream is applied using the spatula supplied with the kit.						
Curing	Curing time depends on the temperature and the thickness applied. At 20°C (68°F) 10 -15 hours. If faster curing is required, heat can be added. At 100°C (212°F) curing time is reduced to 15-20 minutes.						
Chemical Resistance	After curing, Wencon Ceramic Cream will be resistant to oil, water, salt water, most diluted acids and a range of solvents.						
Temperature Resistance	<table> <tr> <td>Corrosion and heavy load:</td> <td>200°C (392°F)</td> </tr> <tr> <td>Light or no load:</td> <td>250°C (482°F)</td> </tr> <tr> <td>As filling compound</td> <td>up to 300°C (572°F)</td> </tr> </table>	Corrosion and heavy load:	200°C (392°F)	Light or no load:	250°C (482°F)	As filling compound	up to 300°C (572°F)
Corrosion and heavy load:	200°C (392°F)						
Light or no load:	250°C (482°F)						
As filling compound	up to 300°C (572°F)						
Specific Volume	538 ccm/kg (34,4 cu inch/kg)						
Hardness	Shore D 80.						
Handling Precautions	Read the instructions on the packaging and the Material Safety Data Sheet.						