

Refurbishment of cavitated Thruster housing

Application:	Repair of Thruster housing
Place:	Farmsum, NL
Date:	September 2016
Job and report done by:	Marine Maintenance Services, NL
Wencon products used:	Ceramic Cream, Ceramic Coating, Cleaner, appl. tools



1.
Shaft of thrust is leaking with a lot of oil,
and by inspection it is clear that the seal has
been exposed to wear. Lead time of the
shaft is approx. 7 weeks.



2.
By dismantling the thruster unit, a lot of
cavitation is discovered in the housing, and
shaft is completely destroyed, due to wear.



3.
Thruster unit is taken into workshop for
sandblasting and complete repair of thruster
housing with Wencon Ceramic Cream and
Wencon Ceramic Coating.



4.
Thruster housing after 5 days of complete
refurbishment, done during dry-docking of
the vessel.



Choose the relevant surface preparation, according to the nature of the job. Seek advice from a Wencon Technician if needed.

Specification for surface preparation for Dry Applications

Defined as applications, where the Wencon product will be applied to a surface at a temperature minimum 3 degrees above dew point. Use the Wencon Products: Wencon Cream, Wencon Rapid, Wencon Coating, Wencon Ceramic Cream, Wencon Ceramic Coating, Wencon Hi-Temp, all requiring a dry surface.

1. Blast the machine part to SA 2 ½ using sharp-edged blasting media, to a roughness of min. 75 microns.
2. Leave the part for sweating out salts in a warm place for at least 12 hours or heat it up to 30 - 40 °C (86-104 °F) using gas torches.
3. Blast again to SA 2 ½ immediately prior to the application.
4. For parts containing lots of water and salt, it may be necessary to repeat 2. and 3. until the surface remains light grey for at least 2 hours after blasting.
5. Always use Wencon Cleaner prior to application.

Specification for surface preparation for Wet/Damp Applications

Defined as applications, where the Wencon product will be applied to a surface at a temperature less than 3 degrees above dew point. Use the products Wencon UW Putty, Wencon UW Cream and Wencon UW Coating for applications on wet or damp surfaces.

1. Water jet the entire surface with water and sand to a standard equal to SA 2½, as described above.

Specification for surface preparation for Emergency/Temporary Applications

Perago Treatment

Perago is a rubber disk with hard steel spikes mounted on the periphery. Perago can be mounted in a normal drilling machine, and gives a surface close to a blasted surface - clean and rough with sharp edges. Perago dishes can be ordered at Wencon and at all Wencon Distributors.

Grinding

Wheel grinding is often an acceptable surface preparation for emergency applications, where shot blasting is not possible. When grinding use a coarse stone or flap. Use the Wencon Cleaner before and after grinding. Grinding with sandpaper or emery cloth is only advisable when, for example, carrying out shaft-repair on a lathe. Often the grinding will not hit the dents.

Needle Gunning

Needle gunning is a method that has almost been forgotten in recent years. Or should we say is mostly used for very rough cleaning or removal of rust. It is possible to do a very nice job using a needle gun, but it takes time and should be closely supervised. It is essential that the marks from the sharp needles cover the whole surface so that none of the original surface remains. It is recommendable to steam clean the surface before needle gunning.

Wire Brushing

Wire brushing can be a good way of removing scales, rust and old paint. However, you will need to grind the surfaces after the wirebrushing to make the surface as rough as possible.