

Wencon Cream

The basic multipurpose epoxy compound for repair and rebuilding of deteriorated metal parts.

- Wide range of applications
- Strong adhesion to all metal surfaces
- Low curing temperature
- Simple mixing and application
- Fully machinable

General information

Wencon Cream is a basic two-component, epoxy compound suitable for a wide range of applications. The compound is for repair and rebuilding of worn, damaged, cracked and corroded metal parts. Wencon Cream is also excellent as a filling compound.

Wencon Cream exhibits many of the characteristics of metals, which together with outstanding adhesion to all metallic surfaces makes the repair compound highly suitable for repair of corroded and worn metals.

Wencon Cream is non conducting and will therefore not cause bi-metallic corrosion. After curing the compound is resistant to oil, water, saltwater and most diluted acids and a range of solvents. Heat resistance ranges from 60° C (140° F) in corrosive and heavy load environments and up to 250° C (482°F) when applied as a filling compound.

Application areas

Typical applications are corroded tanks, pump housings, impellers, valves, pipes, flange faces, roller bearing seats, worn shafts, hydraulic rams and heat exchangers. Wencon Cream is also excellent as a filling compound.

Mixing

Wencon products are designed to be simple to use and cost effective. Easy mixing ratios (1:1 by volume) reduce waste to a minimum and high specific volume gives high coverage rates.



Product numbers:

No. 1010 Wencon Cream, 1 kg (2,2 lb) unit

IMPA no.

812335

ISSA no.

75.553.20

GENERAL DESCRIPTION

Two-component solvent free paste consistency epoxy repair compound.

SURFACE PREPARATION

The surface must always be dry, clean and degreased

Applying to new steel surface:

- shot blasting to SA 2,5
- if shot blasting is not possible use grinding
- after grinding the surface must be degreased with Wencon Bio Cleaner

Repairing old steel surface:

- shot blasting to SA 2,5
- sweat out water and salts
- shot blasting to SA 2,5 again
- profile 75 microns

MIXING RATIO

Mix by volume 1:1. Mix until an even colour is obtained.

POT LIFE

Depending on amount mixed and temperature. Mixed in small amounts, the pot life is approximately 30-60 minutes at 20°C (68°F)

APPLYING

Wencon Cream has a paste consistency and is applied by spatula, also on vertical surfaces.

CURING TIME

Curing will take place in 10-15 hours at 20°C (68°F)

REDUCED CURING TIME WITH INFRARED

This product is tested with and suitable for infrared curing. Curing with infrared radiation can reduce curing time significantly. Result can vary, depending on circumstances and equipment used.

MACHINABILITY

After curing, the product can be machined, drilled and worked like metal.

TECHNICAL DATA

Hardness Shore D: 75 (**DIN 53505**)

Tensile strength: 14,3 N/mm² - 2035 p.s.i. (**DIN 53454**)

Compressive strength:

Modulus of elasticity: 1689 N/mm² - 240,000 p.s.i. (**DIN 53454**)

Rcrack: 58 N/mm² - 8,500 p.s.i. (**DIN 53454**)

Shear adhesion: 14,40 N/mm² - (**ASTM D1002**)

Adhesion to steel: 3,0 N/mm² - (**ISO 4624**)

SPECIFIC VOLUME

775 ccm per kilogramme (49,5 cu inch/kg)

TEMPERATURE RESISTANCE

Corrosion: 60°C (140° F)

Light load: 120°C (248°F)

As filler: 250°C (482°F)

CHEMICAL RESISTANCE

The compound is resistant to oil, water, salt-water and most diluted acids and alkalis as well as a range of solvents.

SHELF LIFE

At 20°C (68°F) : 3 years

HANDLING PRECAUTIONS

Read the Wencon Instruction for Use and the Material Safety Data Sheet.